

SK1N Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration		Swatch Image	State	Length	Width	Height	Units per sqm	Pack Size	Durability Class	Solar Absorption	Lrv	
SK1N	Savio					NSW	500	210	35	11.8	208	Exposure Grade	0.68	22.5
SK1N	Livenza					NSW	500	210	35	11.8	208	Exposure Grade	0.59	43.7
SK1N	Alento					NSW	500	210	35	11.8	208	Exposure Grade	0.32	46.9
SK1N	Potenza					NSW	500	210	35	11.8	208	Exposure Grade	0.67	11.6
SK1N	Piave					NSW	500	210	35	11.8	208	Exposure Grade	0.83	7
SK1N	Tesino					NSW	500	210	35	11.8	208	Exposure Grade	0.61	15.6
SK1N	Chienti					NSW	500	210	35	11.8	208	Exposure Grade	0.79	13.8

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.